


Anisotropic Material made by rapid prototyping technique [polymer]

KSU\_Anisotropic material\_polymer

Specimen 1 to 1



	Tensile stress at Yield (Zero Slope) (MPa)	Modulus (Tangent 0 mm) (MPa)	UTS (MPa)	Maximum Slope (Automatic) (N/mm)
1	-----	975.03560	20.01900	638.46914

	Tensile stress at Break (MPa)
1	34.37671