

(19)



(11)

EP 2 540 746 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
06.03.2013 Bulletin 2013/10

(51) Int Cl.:
C08B 37/00 ^(2006.01) **B01J 45/00** ^(2006.01)
C02F 1/42 ^(2006.01) **C02F 1/28** ^(2006.01)
B01J 20/26 ^(2006.01)

(21) Application number: **11171632.0**

(22) Date of filing: **28.06.2011**

(54) Chitosan derivative, a method for its preparation and its use as an adsorption agent

Chitosan-Derivat, Verfahren zu seiner Herstellung und dessen Verwendung als Adsorptionsmittel

Dérivé de chitosane, procédé pour sa préparation et son utilisation comme agent d'adsorption

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

• **Radwan, Awwad Abdoh**
Riyadh 11333 (SA)

(43) Date of publication of application:
02.01.2013 Bulletin 2013/01

(74) Representative: **Goddar, Heinz J.**
Boehmert & Boehmert
Pettenkofenstrasse 20-22
80336 München (DE)

(73) Proprietor: **King Saud University**
11421 Riyadh (SA)

(56) References cited:
• **A.A. RADWAN ET AL.: "Microwave Irradiation-Assisted Synthesis of a Novel Crown Ether Crosslinked Chitosan as a Chelating Agent for Heavy Metal Ions (M+n)", MOLECULES, vol. 15, 2010, pages 6257-6268, XP002663285,**

(72) Inventors:
• **Al Sarra, Ibrahim Abdallah, Dr.**
Riyadh 11333 (SA)
• **Alanazi, Fars Kaed, Dr.**
Riyadh 11333 (SA)

EP 2 540 746 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to a chitosan derivative, a method for its preparation and its use as an adsorption agent.

5 **[0002]** Heavy metals are highly toxic already at low concentrations and can accumulate in living organisms, causing several disorders and diseases. As a result of industrialization and urbanization, the presence of heavy metal ions in water streams has readily increased in the last 50 years. Removal of heavy metal ions from wastewater is essential because of their extreme environmental, public health, and economic impacts.

10 **[0003]** The main techniques that have been used on metal content reduction from industrial waste are chemical precipitation, ion exchange, membrane filtration, electrolytic methods, reverse osmosis, solvent extraction, and adsorption. However, these methods are limited by high operational cost and/or may also be inefficient in the removal of some toxic metal ions, mainly at trace level concentrations (Evans, J.R. et al, Water Research 2002, 36, 3219-3226; Rangel-Mendez, J.R. et al, J Hazard Mater 2009, 162, 503-511).

15 **[0004]** Some of the best chelation ion-exchange materials consist of different biopolymers and their derivatives because of the variety of functional groups, like -OH and -NH₂, with which several compounds, e.g., metal ions, can easily react or be bound. These biopolymers, including cellulosics, alginates, proteins, chitin, and chitin derivatives, have remarkable capabilities of lowering metal ion concentrations to parts per billion levels. For example, chitosan (CTS), a deacetylation derivative of chitin, can adsorb metals owing to its amino and hydroxyl groups. However, CTS can be dissolved in acidic media so it limits its recycling in adsorption processes. Crosslinked chitosan synthesized by the reaction of CTS with hydrophobic crosslinking agents can overcome this disadvantage of CTS and still keep good adsorption properties for many metal ions. Also, modifications to increase the number of binding sites and/or binding surfaces of chitosan have been made both by substitution on the amino group at C-2 or by crosslinking the polyglycans with suitable agents.

20 **[0005]** Crosslinking CTS with biomass/biopolymers like alginate, chelators like ethylenediamine tetraacetic acid (EDTA), fixatives like glutaraldehyde (GA) or polymers like polyvinyl alcohol (PVA), creates a three-dimensional network within the biopolymer and increases the internal surface area for metal adsorption.

25 **[0006]** Increase in structural and chemical stability of these cross-linked derivatives contributes to the resistance and endurance towards acid from surface and subsurface groundwater, thereby improving water/sewage purification treatments.

30 **[0007]** Crown ethers have good and different complex selectivity for many metal ions. Unfortunately, they can not be recycled easily after utilization. Therefore, their applications are limited. If crown ethers are crosslinked to chitosan, these novel chitosan derivatives have stronger complex formation with better selectivity for metal ions than corresponding crown ethers and chitosan separately (Yi, Y. et al, Carbohydrate Polymers 2003, 53, 425-430).

[0008] A.A. Radwan et al., Molecules 2010, 15, 6257-6268 discloses the preparation of a Schiff base type cross-linked chitosan crown ether and its use for the complexation of heavy metal ions.

35 **[0009]** It is an object of the present invention to provide a chitosan derivative which overcomes the drawbacks of the prior art, especially exhibiting an enhanced porosity, a high chemical stability, especially an increased resistance to dissolution in acidic media, an increased adsorption capacity for metal ions and an easy and efficient recyclability.

[0010] Further, a method for the preparation of chitosan derivatives shall be provided.


[0011] Finally, it is a further object of the invention to provide easy use of these chitosan derivatives.

40 **[0012]** The first object is achieved by a chitosan derivative having the repeating unit of formula 1

45

50

55



Scheme 1

wherein step (i) takes place in the presence of zinc chloride and an organic solvent in a temperature range from 50-150°C, preferably in a temperature range from 75-125°C, preferably, in a temperature range from 100-110°C.

[0015] The cross-linked chitosan crown ether compound (7) can be prepared according to literature, such as A.A. Radwan et al., *Molecules* 2010, 15, 16257-16268 according to the following scheme:

5


10

15

20

25

30



[0016] Preferably, the alpha-mercaptocarboxylic acid is mercaptoacetic acid.

35

[0017] Also preferred the beta-mercaptocarboxylic acid is beta-mercaptopropionic acid.

[0018] Preferably the organic solvent is 1,4-dioxane.

[0019] In a preferred embodiment step (i) takes place under microwave irradiation.

[0020] In another preferred embodiment, the power of the microwave irradiation is in a range from 30-300 W, preferably in a range from 50-150 W, preferably in a range from 75-85 W.

40

[0021] It is also preferred that the irradiation time is in a range from 1-60 min, preferably in a range from 5-30 min, preferably 10 min.

[0022] Finally, according to the invention is the use of the chitosan derivative according to formula 1 for the adsorption of metal ions.

[0023] In a preferred embodiment the metal ions are heavy metal ions.

45

[0024] More preferred the metal ions are silver, gold, platinum, lead and/or mercury ions.

[0025] Most preferred the metal ions are lead and/or mercury ions.

[0026] More preferred the acid used for acidic treatment is diluted hydrochloric acid.

[0027] In another preferred embodiment, the metal ions are removed from water, preferably waste water, more preferably industrial waste water.


50

[0028] In a preferred embodiment the chitosan derivative of the formula 1 is used for the separation of mercury ions from other metal ions by selective adsorption.

[0029] It is obvious to one skilled in the art in knowledge of A.A. Radwan et al., *Molecules* 2010, 15, 6257-6268 that the compound of the formula 7 can be easily achieved by the reaction of a crown ether of the formula 6 and chitosan.

55

[0030] It is also obvious that the terminal dashes in the formula of the fragments A do not represent methyl groups but options for binding to the chitosan or the crown ether. This can be best accomplished by the following detailed example of a chitosan derivative falling under formula 1:



30 **[0031]** Surprisingly, it was found that the thiazolidinone derivatives of crown ether cross-linked chitosan according to the invention overcome the drawbacks of the prior art by exhibiting higher porosity, being insoluble in acidic solutions and featuring increasing binding affinity towards metal ions compared to chitosan or other crown ether cross-linked chitosan known for this proposal.

35 **[0032]** Also, the inventors of the present application have surprisingly found an easy method for the preparation of thiazolidinone derivatives of crown ether cross-linked chitosan by the reaction of mercaptocarboxylic acids with a Schiff type cross-linked crown ether chitosan, and that the reaction can be carried out thermally as well as under microwave irradiation.

40 **[0033]** Finally, it was surprisingly found that after the adsorption of metal ions the thiazolidinone derivatives of crown ether cross-linked chitosan according to the present invention can be recycled several times by acidic treatment and subsequent filtration and washing. This easy recycling procedure is feasible due to the surprising low solubility in acidic aqueous media.

45 **[0034]** The invention will now be described in more detail by the following examples to exemplify the invention, with reference to the accompanying drawing wherein Fig. 1 illustrates a scanning electron microscopy image of CTdBE according to the present invention. The examples, however, are not intended to have limiting effect on the subject-matter of the claims or on the scope of protection.

EXAMPLE 1

Preparation of cross-linked thiazolidinone chitosan dibenzo crown ether (CTdBE)

50

Method a:

55 **[0035]** Schiff base type cross-linked chitosan dibenzocrown ether (CCdBE) (1 g) was mixed with 1 g of mercaptoacetic acid in a 250 ml round bottom flask containing 10 ml of 1,4-dioxane and 20 mg of zinc chloride. After refluxing overnight the reaction mixture was cooled, filtered and the obtained residue washed with water several times and subsequently dried under reduced pressure overnight, giving brownish-beige solid.

Method b:

[0036] Mercaptoacetic acid (1 g) was added to CCdBE (1 g). The reaction mixture was irradiated in a microwave oven (MW domestic type oven 800W DAEWOO) at 10 % intensity for 10 min. After cooling to room temperature the residue was filtered and washed with water. The residue was dried under reduced pressure overnight giving beige fibrous solid.

[0037] Solid state ^{13}C NMR spectra were done, at Center for Pharmaceutical Biotechnology University of Illinois at Chicago USA, on a Broker Avance operating at 500 MHz ^1H frequency with a Broker magic angle spinning probe with 4 mm diameter rotors. CPMAS spectra were collected at 9 kHz spinning speed and 55 kHz Two-Pulse Phase Modulation (TPPM) decoupling. Cross Polarization Magic Angle Spinning (CPMAS) spectrum of sample CTdBE is obtained. Conclusions that can be drawn from the spectra are listed in bullet point format below that lead to a reasonable conclusion that the thiazolidinone ring is formed in sample CTdBE.

- The spectrum shows carbonyl carbons between 180 and 170 ppm and methyl carbons at ~25 ppm. This is consistent with incomplete deacylation of chitosan.
- Linewidths are between 200 Hz and 800 Hz which is consistent with amorphous compounds and previously published work on Chitosan.
- There is some decrease in the C=N signal at ~150 ppm, as well as the appearance of an unassigned peak at ~30 ppm.
- The peak at ~30 ppm would be consistent with the carbon in the thiazolidinone ring.
- There is an overall increase in signal in the carbonyl region of the spectrum (~170 ppm), which would be consistent with the addition of the thiazolidinone ring.

EXAMPLE 2

[0038] Scanning electron microscope image of the surface morphology of CTdBE shows a highly porous, pocket shaped surface. This property enhances the adsorption capacity of these compounds to heavy metals compared to the precursor chitosan itself. A respective SEM image of a chitosan derivative according to the present invention is shown in Fig. 1.

EXAMPLE 3**Single Metal Ion Adsorption Experiment**

[0039] 25 mg of CTdBE were added to 100.0 mL of metal acetate solution (initial M^{2+} concentration 10 ppm) with a given pH (pH 4 and pH 6) adjusted with 0.1 M acetic acid, shaken for 24 h at 25 °C and then filtered. The adsorption capacities for metal ions were determined from initial and final concentration of metal ions in the acetate solution determined by atomic absorption spectrophotometry.

[0040] Table 1 summarizes up the *Single metal ion* adsorption capacities of CTdBE for Pb^{2+} and Hg^{2+} which is much higher than that of natural chitosan CTS or the previously reported Schiff base type cross-linked crown ether chitosan CCdBE. This is attributed to that the three-dimensional network of CTdBE provides a cavity tailored to the volumetric space of Pb^{2+} and Hg^{2+} to adsorption.

Table 1. Adsorption capacities of CTS, CCdBE and CTdBE for Pb^{2+} and Hg^{2+} , each at pH 4 and pH 6.

Adsorbent	Adsorption capacities (mmol/g)			
	pH 4		pH 6	
	Pb^{2+}	Hg^{2+}	Pb^{2+}	Hg^{2+}
CTdBE	1.10	1.31	1.38	1.78
CTS	0.82	0.33	0.94	1.48
CCdBE	0.99	1.10	1.18	1.58

EXAMPLE 4

Two Metal Ions co-Adsorption Experiment

5 [0041] 25 mg of CTdBE were added to 100.0 mL of metal acetate solution containing Pb^{2+} and Hg^{2+} ions (initial concentration of single species 5 ppm) at pH 4 and at pH 6, shaken for 24 h at 25 °C and then filtered. The contents of M^{2+} were determined from initial and final concentration of metal ions in the acetate solution determined by atomic absorption spectrophotometry.

10 [0042] Two metal ions (Pb^{2+} and Hg^{2+}) co-adsorption results are shown in Table 2. By comparing the selectivity of adsorption of the compound CTdBE with that of compounds CCdBE and CTS, it is found that the adsorption of CTdBE for Hg^{2+} is of higher priority than Pb^{2+} at pH 4 and pH 6 as seen from the results of selectivity coefficient ($K_{Hg/Pb}$) in Table 2. The results further suggest that CTdBE can selectively recognize Hg^{2+} , and it is concluded that a selective separation of Pb^{2+} and Hg^{2+} is affected by using an CTdBE better than CCdBE and CTS.

15 **Table 2.** Adsorption selectivity of CTS, CCdBE and CTdBE for Pb^{2+} and Hg^{2+}

Adsorbent	Adsorption capacities (mmol/g)		Selectivity coefficient ($K_{Hg^{2+}/Pb^{2+}}$)	Adsorption capacities (mmol/g)		Selectivity coefficient ($K_{Hg^{2+}/Pb^{2+}}$)
	pH 4			pH 6		
	Pb^{2+}	Hg^{2+}		Pb^{2+}	Hg^{2+}	
20 CTdBE	0.11	1.79	16.27	0.12	2.39	19.92
CTS	0.29	0.13	0.45	0.42	0.57	1.36
CCdBE	0.12	0.96	8.00	0.13	1.38	10.62

25

EXAMPLE 5

Reusability Experiment

30 [0043] The crosslinked chitosan CTdBE after adsorption of Pb^{2+} was stirred in 0.1 M HCl for 1 h at 25 °C to remove Pb^{2+} , and then was treated with 0.1 M NaOH for 5-8 h. Finally it was filtered and washed with water, ethanol and ether in turn. The CTdBE obtained this way was used in adsorption experiment, and the process was repeated 10 times.

35 [0044] It is observed that the adsorption capacities of CTdBE for Pb^{2+} slightly decreases only after of reuse as high as 10 times. Fortunately, CTdBE changed into sponge shape when left in aqueous solutions at different pHs without any dissolution properties. This property is advantageous in collecting of CTdBE after use and ease of its filtration and dryness followed by extraction of the adsorbent in acidic medium. Repeat of filtration and drying provides CTdBE for a reuse again. This property suggests the invented compound CTdBE for practical application as adsorbent of heavy metals. The practicability of its application arises from its economical usefulness as the starting material for synthesis as chitosan is cheap and naturally occurring and secondly because of its reusability several times in addition to its adsorption capacity and selectivity which is ten times higher than that of CTS itself which is practically in current use as adsorbent.

40 [0045] The features disclosed in the foregoing description, in the claims and the drawing may both separately and in any combination thereof be material for realizing the invention in diverse forms thereof.


45

Claims


1. Chitosan derivative having the repeating unit of formula 1

50

55



wherein each A is independently selected from



A is vicinally bound to the crown ether,
n equals 1 or 2,

X is selected from CHR_4 , NH, O or S,

Y is selected from CR_4 or N,


L is selected from CR_5 or N,

R_1 , R_2 , R_3 , R_4 and R_5 are independently selected from hydrogen, halogen, C_1 - C_{20} -alkyl, C_1 - C_{20} -alkoxy, mercapto, alkylthio, alkylamino, arylthio, heteroarylthio, arylamino and heteroarylamino.

2. Method for preparing a chitosan derivative according to claim 1, comprising the step:

i) reacting a cross-linked chitosan crown ether (7) with an alpha-mercapto carboxylic acid and/or a beta-mercapto carboxylic acid to result in a chitosan derivative (1), according to the following scheme 1:

5
10
15
20
25
30
35
40
45



Scheme 1

wherein step (i) takes place in the presence of zinc chloride and an organic solvent in a temperature range from 50-150°C.

- 3. Method according to claim 2, wherein the alpha-mercaptocarboxylic acid is mercaptoacetic acid.
- 4. Method according to claim 2, wherein the beta-mercaptocarboxylic acid is beta-mercaptopropionic acid.
- 5. Method according to any of the claims 2-4, wherein the organic solvent is 1,4-dioxane.
- 6. Method according to any of the claims 2-5, wherein step (i) takes place under microwave irradiation.
- 7. Method according to claim 6, wherein the power of the microwave irradiation is in a range from 30-300 W.

8. Method according to claim 6 or 7, wherein the irradiation time is in a range from 1-60 min.
9. Use of the chitosan derivative according to claim 1 for the adsorption of metal ions.
- 5 10. Use according to claim 9, wherein the metal ions are heavy metal ions.
11. Use according to claim 9 or 10, wherein the chitosan derivative is recycled after adsorption by removal of the metal ions via acidic treatment.
- 10 12. Use according to any of claims 9-11, wherein the metal ions are removed from water.
13. Use of the chitosan derivative according to claim 9 for the separation of mercury ions from other metal ions by selective adsorption.

15

Patentansprüche

1. Chitosan-Derivat mit einer Wiederholungseinheit der Formel 1

20


25

30

35


40

45



wobei jedes A unabhängig ausgewählt ist aus

50



55

A vicinal zum Kronenether gebunden ist,
n gleich 1 oder 2 ist,

EP 2 540 746 B1

X ausgewählt ist aus CHR_4 , NH, O oder S,

Y ausgewählt ist aus CR_4 oder N,

L ausgewählt ist aus CR_5 oder N,

R_1, R_2, R_3, R_4 und R_5 unabhängig ausgewählt sind aus Wasserstoff, Halogen, $\text{C}_1\text{-C}_{20}$ -Alkyl, $\text{C}_1\text{-C}_{20}$ -Alkoxy, Mercapto, Alkylthio, Alkylamino, Arylthio, Heteroarylthio, Arylamino und Heteroarylamino.

5

2. Verfahren zur Herstellung eines Chitosan-Derivats nach Anspruch 1, umfassend den Schritt:

i) Reagieren eines vernetzten Chitosan-Kronenethers (7) mit einer alpha-Mercaptocarboxylsäure und/oder einer beta-Mercaptocarboxylsäure, um ein Chitosan-Derivat (1) zu erhalten, gemäß dem folgenden Schema 1:

10

15

20

25

30


35

40

45

50


55



Schema 1

wobei Schritt (i) in Gegenwart von Zinkchlorid und einem organischen Lösungsmittel in einem Temperaturbereich

5



10

A est lié vicinalement à l'éther couronne,

n est égal à 1 ou 2,

X est choisi parmi CHR₄, NH, O ou S,

Y est choisi parmi CR₄ ou N,

L est choisi parmi CR₅ ou N,

15

R₁, R₂, R₃, R₄ et R₅ sont indépendamment choisis parmi un hydrogène, un halogène, un alkyle en C₁ à C₂₀, un alkoxy en C₁ à C₂₀, un mercapto, un alkylthio, un alkylamino, un arylthio, un hétéroarylthio, un arylamino et un hétéroarylamino.

20

2. Procédé destiné à préparer un dérivé de chitosane selon la revendication 1, comprenant l'étape consistant

i) à faire réagir un éther couronne de chitosane réticulé (7) avec un acide alpha-mercapto-carboxylique et/ou un acide bêta-mercapto-carboxylique pour conduire à un dérivé de chitosane (1), selon le schéma 1 suivant :

25

30

35

40

45

50

55




Schéma 1

dans lequel l'étape (i) est effectuée en présence de chlorure de zinc et d'un solvant organique dans une plage de température allant de 50 à 150°C.

- 40
- 45
- 50
- 55
3. Procédé selon la revendication 2, dans lequel l'acide alpha-mercapto-carboxylique est de l'acide mercapto-acétique.
 4. Procédé selon la revendication 2, dans lequel l'acide bêta-mercapto-carboxylique est de l'acide bêta-mercapto-propionique.
 5. Procédé selon l'une quelconque des revendications 2-4, dans lequel le solvant organique est le 1,4-dioxine.
 6. Procédé selon l'une quelconque des revendications 2-5, dans lequel l'étape (i) est effectuée sous une irradiation par micro-ondes.
 7. Procédé selon la revendication 6, dans lequel la puissance de l'irradiation par micro-ondes est dans la plage allant de 30 à 300 W.
 8. Procédé selon la revendication 6 ou 7, dans lequel la période d'irradiation est dans une plage allant de 1 à 60 min.
 9. Utilisation du dérivé de chitosane selon la revendication 1, pour l'adsorption des ions métalliques.
 10. Utilisation selon la revendication 9, dans laquelle les ions métalliques sont des ions métalliques lourds.

EP 2 540 746 B1

11. Utilisation selon la revendication 9 ou 10, dans laquelle le dérivé de chitosane est recyclé après adsorption par élimination des ions métalliques via un traitement acide.
12. Utilisation selon l'une quelconque des revendications 9-11, dans laquelle les ions métalliques sont éliminés de l'eau.
13. Utilisation du dérivé de chitosane selon la revendication 9 pour la séparation des ions mercure à partir d'autres ions métalliques par adsorption sélective.

5

10

15

20

25

30

35

40

45

50

55




FIG. 1

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Non-patent literature cited in the description

- **EVANS, J.R. et al.** *Water Research*, 2002, vol. 36, 3219-3226 [0003]
- **RANGEL-MENDEZ, J.R. et al.** *J Hazard Mater*, 2009, vol. 162, 503-511 [0003]
- **YI, Y. et al.** *Carbohydrate Polymers*, 2003, vol. 53, 425-430 [0007]
- **A.A. RADWAN et al.** *Molecules*, 2010, vol. 15, 6257-6268 [0008] [0029]
- **A.A. RADWAN et al.** *Molecules*, 2010, vol. 15, 16257-16268 [0015]